

PRODUCT DATA SHEET

SikaTile[®]-340 Standard

STANDARD TILE ADHESIVE FOR CERAMIC AND GRANITO

DESCRIPTION

SikaTile[®]-340 Standard is a general cement-based tile adhesive for ceramic and clay tile with a single component, pre-packed tiling adhesive mortar combining cement with selected grades of sand and several additives. Only requires the addition of water.

USES

- Perfect for ceramic floor and wall tiles. Interior and exterior use.
- Suitable for porcelain and granito tiles up to 60x60 cm. Interior floor and wall installation.
- Can be used for porcelain, granito tiles, exterior floor installation only.
- Substrates: Cement. It is also suitable for tiling onto waterproof membranes in wet areas. (Upon testing with our technical team before application).

FEATURES

- Good bonding strength.
- Extended open time resulting in faster application
- Tile can be adjusted after laying within 15 minutes
- Smooth and easy to use
- Low VOCs

CERTIFICATES AND TEST REPORTS

ANSI 118.1

PRODUCT INFORMATION

| | |
|-----------------------|--|
| Composition | Hydraulic binder, mineral filler, polymer, and additives |
| Packaging | 20 kg/ bag |
| Appearance and colour | Grey powder |
| Shelf life | 12 months from date of production if stored in undamaged and unopened, original sealed packaging |
| Storage conditions | Store in dry condition and protected from direct sunshine |
| Density | 1.4 ± 0.1 kg/L |
| pH-Value | 12 ± 1 |

TECHNICAL INFORMATION

| | | |
|---------------------------|------------|-----------------------|
| Tensile adhesion strength | At 28 days | EN 12004 ISO 13007 |
| | Initial | |
| Slip resistance | ≤ 0.5 mm | |

Shear adhesion strength**Glazed Wall Tile**

ANSI 118.1

| | |
|------------------------|------------|
| 7 days | ≥ 1.38 MPa |
| 7 days water immersion | ≥ 1.03 MPa |

Porcelain Mosaic Tile

ANSI 118.1

| | |
|------------------------|------------|
| 1 day | ≥ 0.34 MPa |
| 7 days | ≥ 1.03 MPa |
| 7 days water immersion | ≥ 0.69 MPa |
| 28 days | ≥ 1.03 MPa |
| 12 weeks | ≥ 1.03 MPa |

APPLICATION INFORMATION

| | | | | |
|--|--|--|--------------------------------------|----------------------------|
| Mixing ratio | Approximate 4.6 to 5.0 litre water per bag 20 kg | | | |
| Consumption | Trowel Size | Tile Size (cm x cm) | Tile Surface (cm²) | Consumption (20 kg) |
| | 3 mm | 2.5 x 2.5 5 x 5 | 6.25 | 7 - 8 m ² |
| | 6 mm | 10 x 10 20 x 20 20 x 25 30 x 30 | 100 400 500 900 | 5 - 6 m ² |
| | 9 mm | 40 x 40 50 x 50 60 x 60 > 60 x 60 | 1,600 2,500 3,600 > 3,600 | 2 - 3 m ² |
| <p>Note :</p> <p>1. This is an average calculation. Actual usage may differ from the estimate. Due to the different surface conditions. Surface absorption and the purpose of the individual's use.</p> <p>2. For tile sizes larger than 40x40 cm, apply tile adhesive on the surface and a very thin layer on the back of the tile.</p> | | | | |
| Ambient air temperature | +5°C to +35°C | | | |
| Pot Life | 180 - 240 minutes (at 25°C) | | | |
| Open Time | 20 - 25 minutes (at 25°C) | | | |
| Applied product ready for use | ~ 24 hours | | | |
| Adjustability time | 15 - 20 minutes (at 25°C) | | | |

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Maximum weight of tile for interior wall application is 30 kg/ m².
- Use a proper notched trowel to spread the adhesive onto the substrate with the flat side of the trowel until it is smooth.
- Use the notched side of the trowel to create an even adhesive bed. The minimum bed thickness is
 - 2 mm. for wall
 - 3 mm. for floor
 (size depends on the thickness of tiles)

- Ensure the adhesive is wet when the tiles are laid and tapped into the position to ensure full contact with the adhesive. Do not spread more than 1 sqm at once.
- Once the tiles have been laid, leave them to stand for 24 hours or until the tile adhesive is dry before grouting with SikaTile Tile Grout.
- Refer to the Safety Data Sheet.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage, and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological, and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- Substrate should be sound, clean, and without any trace of oil. The level should be considered.
- Painted surfaces must be abraded to expose at least 80% of the original substrate.
- New concrete must be allowed to cure at least 28 days.
- New render must be allowed to cure at least 7 days per 1 cm of thickness.
- Dampen the substrate to decrease water absorption before tiling

MIXING

- Mix SikaTile®-340 Standard 20 kg with 4.6 - 5.0 Litres of clean water with electrical mixer until the compound is evenly distributed.
- Allow the mixture to stand for 2 - 3 minutes for a good reaction and reduce air bubbles before using the adhesive.

APPLICATION

- Spread tile adhesive by using a notched trowel onto the substrate.
- Fix tile on tile adhesive and knock it over with a rubber hammer.
- Dual bonding should be applied when the tile size is larger than 25 cm x 25 cm. Apply a thin layer of tile adhesive onto the back of the tile, then fix the tile onto the adhesive substrate.
- Once the tiles have been laid, leave them to stand for 24 hours or until the tile adhesive is dry before grouting with SikaTile Tile Grout.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited

700/37 Moo 5 Amata City Chonburi
Industrial Estate, T. Klong Tamhru
A. Muang, Chonburi 20000, Thailand
Tel : +66 3810 9500
E-mail : sikathai@th.sika.com
Website: tha.sika.com



Product Data Sheet

SikaTile®-340 Standard
November 2025, Version 02.01
021710101000000135

SikaTile-340Standard-en-TH-(11-2025)-2-1.pdf