

PRODUCT DATA SHEET

SikaTile®-350 Performance

QUALITY TILE ADHESIVE FOR PORCELAIN AND GRANITO TILE



DESCRIPTION

SikaTile®-350 Performance is a standard cement-based tile adhesive with polymer-modified as a single component, pre-packed tiling adhesive mortar combining cement with selected grades of sand and several additives. Only requires the addition of water.

USES

- Perfect for granito tiles up to 90x90 cm on interior floor and wall installation.
- Can be used for large-sized granito tile for exterior floor installation only.
- General ceramic tile. Both interior and exterior floor and wall installation.
- Substrates: Cement. It is also suitable for tiling onto waterproof membranes in wet areas.

FEATURES

- Dedicated to granito and low porous tiles
- Excellent bonding strength
- Extended open time resulting in faster application
- Tile can be adjusted after laying within 15 minutes
- Smooth and easy use

SUSTAINABILITY

- LEED v4 and v4.1 BETA
- WELL Building Standard™

CERTIFICATES AND TEST REPORTS

- EN 12004 C1TE
- ANSI 118.1
- TIS 2703-2559

PRODUCT INFORMATION

Composition	Hydraulic binder, mineral filler, polymer, and admixtures
Packaging	20kg/ bag
Shelf life	12 months from date of production if stored in undamaged and unopened, original sealed packaging
Storage conditions	Store in dry condition and protected from direct sunshine
Appearance and colour	Grey powder
Density	1.3 ± 0.1 kg/L
pH-Value	12 ± 1

TECHNICAL INFORMATION

Tensile adhesion strength**At 28 days**

Initial	≥ 0.5 MPa
Water immersion	≥ 0.5 MPa
Heat aging	≥ 0.5 MPa
Open time bonding after 20 min	≥ 0.5 MPa
Extended open time after not less than 30min	≥ 0.5 MPa

EN 12004 C1TE
ISO 13007**Shear adhesion strength****Glazed Wall Tile**

7 days	≥ 1.38 MPa
7 days water immersion	≥ 1.03 MPa

ANSI 118.1

Porcelain Mosaic Tile

1 day	≥ 0.34 MPa
7 days	≥ 1.03 MPa
7 days water immersion	≥ 0.69 MPa
28 days	≥ 1.03 MPa

ANSI 118.1

Slip resistance

≤ 0.5 mm

APPLICATION INFORMATION**Consumption**

Trowel Size	Tile Size (cm x cm)	Tile Surface (cm ²)	Consumption (20 kg)
3 mm	2.5 x 2.5	6.25	7 - 8 m ²
	5 x 5	25	
6 mm	10 x 10	100	5 - 6 m ²
	20 x 20	400	
	20 x 25	500	
	30 x 30	900	
9 mm	40 x 40	1,600	2 - 3 m ²
	50 x 50	2,500	
	60 x 60	3,600	
	>60 x 60	>3,600	

Note :

1. This is an average calculation. Actual usage may differ from the estimate. Due to the different surface conditions. Surface absorption and the purpose of the individual's use.
2. For tile sizes larger than 40x40 cm, apply tile adhesive on the surface and a very thin layer on the back of the tile.

Ambient air temperature

+5°C to +35°C

Mixing ratio

Approximate 4.8 to 5.6 litre water per bag 20 kg

Pot Life

180 - 240 minutes (at 25°C)

Open Time

20 - 25 minutes (at 25°C)

Adjustability time

15 - 20 minutes (at 25°C)

Applied product ready for use

~ 24 hours

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Maximum weight of tile for interior/ exterior wall application is 30 kg/ m².
- Use a proper notched trowel to spread the adhes-

ive onto the substrate with the flat side of the trowel until it is smooth.

- Use the notched side of the trowel to create an even adhesive bed. The minimum bed thickness is 2 mm for the wall and 3 mm for the floor. (size depends on the thickness of tiles)
- Ensure the adhesive is wet when the tiles are laid and tapped into the position to ensure full contact with the adhesive. Do not spread more than 1 sqm at once.

- Once the tile adhesive is dry before grouting with SikaTile Tile Grout.
- Refer to the Safety Data Sheet.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- Substrate should be sound, clean, and without any trace of oil. The level should be considered.
- Painted surfaces must be abraded to expose at least 80% of the original substrate.
- New concrete must be allowed to cure at least 28 days.
- New render must be allowed to cure at least 7 days per 1 cm of thickness.
- Dampen the substrate to decrease water absorption before tiling.

MIXING

- Mix SikaTile®-350 Performance 20 kg with 4.8 - 5.6 Litres of clean water with an electrical mixer until the compound is evenly distributed.
- Allow the mixture to stand for 2 - 3 minutes for a good reaction and reduce air bubbles before using the adhesive.

APPLICATION

- Spread tile adhesive by using a notched trowel onto the substrate.
- Fix tile on tile adhesive and knock it over with a rubber hammer.
- Dual bonding should be applied when the tile size is larger than 25 cm x 25 cm. Apply a thin layer of tile adhesive onto the back of the tile, then fix the tile onto the adhesive substrate.
- Once the tiles have been laid, leave them to stand for 24 hours or until the tile adhesive is dry before grouting with SikaTile Tile Grout.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited

700/37 Moo 5 Amata City Chonburi
Industrial Estate, T. Klong Tamhru
A. Muang, Chonburi 20000, Thailand
Tel : +66 3810 9500
E-mail : sikathai@th.sika.com
Website: tha.sika.com



Product Data Sheet

SikaTile®-350 Performance
August 2024, Version 01.02
021710102000001034

SikaTile-350Performance-en-TH-(08-2024)-1-2.pdf