

Sika® Skim Coat

Powder for Surface Finishing

Product Description	Sika® Skim Coat is a mixture of powder to be mixed with water for repairing surface defects in concrete or render. A smooth surface is obtained by eliminating blemishes such as grooves, seams, fine cracks and rock pockets.
Uses	Sika® Skim Coat when mixed with water is a surface finishing coating for reinforced concrete surfaces, precast concrete panels, brick and block works etc.
Characteristics / Advantages	Sika Skim® Coat can be applied to both interior and exterior substrates. Sika Skim® Coat has the following advantages; <ul style="list-style-type: none">■ Durable hard wearing surface■ Easy to use■ Excellent bonding to cementitious substrates■ Quick application time
Form	
Appearance	Powder
Colour	Grey, White
Packaging	20 kg/bag
Storage	
Storage Conditions/ Shelf Life	In unopened bag if store at protected area from direct sunshine in dry condition 9 months.
Technical Data	
Bulk Density	~1.4 kg/l
Particle Size	Max. 0.1 mm



System Information

Application Details

Consumption

Approx. 1.9 kg/m²/1 mm thickness

Substrate Preparation

The substrates must be clean, sound and free from loose particles. Dust and oil must be removed before application.

Application

Mix Sika® Skim Coat with water until a homogenous mixture is achieved. Leave the mixture to stand for several minutes.

- For grey color, use water 7.0-7.4 litres (35%-37%) per 1 bag of Sika® Skim Coat (20 kg)
- For white color, use water 7.4-7.8 litres (37%-39%) per 1 bag of Sika® Skim Coat (20 kg)

Apply the mixture to the prepared substrate with trowel or putty knife. One or more coats may be applied depending on the desired finish.

The application thickness is approx. 0.5 - 2.0 mm.

The surface of Sika® Skim Coat can be sanded.

Pot Life

Approximately 45 minutes at 30°C

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited

Head Office

700/37 Moo 5 • Amata Nakorn Estate
Bangna-Trad KM.57 • Tambol Klong Tamhru
Muang District • Chonburi • 20000 Thailand

Tel : +66 3810 9500

Fax : +66 3821 4286

E-mail : sikathai@th.sika.com

www.sika.co.th

Sika® Skim Coat 2/2

