

# PRODUCT DATA SHEET

## TONG-TP6

Cement additive for air entrainment and masonry cement

### DESCRIPTION

TONG-TP6 is a liquid cement additive that has been specifically formulated to provide air entrainment to masonry cements.

### USES

Increase the entrained air property

### CHARACTERISTICS / ADVANTAGES

TONG-TP6 provides the following characteristics:

- Proven performance and control of entrained air;
- Improved handling and flow characteristics;
- Improved plasticity and workability;
- Reduced shrinkage and segregation.

### PRODUCT INFORMATION

<b>Packaging</b>	1,000 kg IBC
<b>Shelf life</b>	12 months in undamaged, unopened and sealed original containers
<b>Storage conditions</b>	Stored at temperatures between +5°C and +35°C. Protect from frost, direct sunlight and contamination. Note: When delivered in bulk, the tanks and equipment used must be free from contaminants.
<b>Appearance and colour</b>	Colourless to slightly yellow liquid
<b>Density</b>	1.020 - 1.040 kg/L (at +25°C)
<b>pH-Value</b>	9.5 - 11.5
<b>Recommended dosage</b>	TONG-TP6 is to be added into the grinding mill (first compartment) or onto the clinker and limestone (raw material) on the conveyor belt. Typical dosage rates of TONG-TP6 are between 0.3 – 1.0 kg per ton of cement (0.03% - 0.10 % of total weight = cement clinker + additions). The optimum dosage to achieve the desired characteristics shall be determined in plant trials. Influencing factors are e.g. the properties of clinker source, type of cement and other plant variables as well as other raw materials. For consistent results, TONG-TP6 must be accurately dispensed with suitable calibrated equipment.
<b>Dispensing</b>	TONG-TP6 is added onto the clinker feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing. Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked!

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika (Thailand) Limited

700/37 Moo 5 Amata City Chonburi  
Industrial Estate, T. Klong Tamhru  
A. Muang, Chonburi 20000, Thailand  
Tel : +66 3810 9500  
E-mail : sikathai@th.sika.com  
Website: tha.sika.com



### Product Data Sheet

TONG-TP6

May 2023, Version 01.01  
021407031002000002

TONG-TP6-en-TH-(05-2023)-1-1.pdf