

PRODUCT DATA SHEET

SikaGrind®-840

EFFICIENT GRINDING AID FOR THE PRODUCTION OF CEMENT

DESCRIPTION

SikaGrind®-840 is a chloride free, liquid cement additive.

SikaGrind®-840 is powered by Sika® ViscoCrete® to optimize the efficiency of modern separators and cement mills.

USES

- Increae the production rate of cement
- Reduce the risk of brown discolouration

CHARACTERISTICS / ADVANTAGES

SikaGrind®-840 is powered by Sika® ViscoCrete® to optimize the efficiency of modern separators and cement mills. provides the following advantages in the cement production:

- Increased production rate
- Easier achievement of the desired cement fineness
- Cost savings due to lower specific power consumption per ton

SikaGrind®-840 is powered by Sika® ViscoCrete® to optimize the efficiency of modern separators and cement mills. provides the following advantages to the finished cement:

- Increased early strength
- Improved powder flow characteristics

APPROVALS / CERTIFICATES

SikaGrind®-840 is produced under Quality management systems according to EN ISO 9001.

PRODUCT INFORMATION

Composition	Blend of polycarboxylates and glycols
Packaging	1000 kg IBC
Appearance / Colour	Clear Yellowish Liquid
Shelf life	At least 12 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Stored at temperatures between +5°C and +35°C. Protect from frost, direct sunlight and contamination. Note: When delivered in bulk, the tanks and equipment used must be free from contaminants.
Density	1.07 ± 0.03 kg/l (at 25°C)
pH-Value	3.0 ± 1.0 (at 25°C)

Product Data Sheet SikaGrind®-840 August 2018, Version 01.02 021407011000000065 < 0.1 M%

APPLICATION INFORMATION

Recommended Dosage	Typical dosage rates of SikaGrind®-840 are between 0.2 - 0.5 kg per ton of cement (0.02% - 0.05% of total weight = cement clinker + additions). The optimum dosage to achieve the desired characteristics shall be determined in plant trials. Influencing factors are e.g. the properties of clinker, type of cement and other plant variables. For consistent results, SikaGrind®-840 must be accurately dispensed.
Compatibility	Cements treated with SikaGrind®-840 are compatible in concretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-840.
Dispensing	SikaGrind®-840 shall be added onto the clinker feed shortly before the mill entrance or directly into the grinding mill. Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing. Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited

700/37 Moo 5 Amata City Chonburi KM.57 Bangna Trad Rd., T. Klong Tamhru A. Muang, Chonburi 20000, Thailand Tel: +66 3810 9500 E-mail: sikathai@th.sika.com









Product Data Sheet SikaGrind®-840 August 2018, Version 01.02 021407011000000065



