

PRODUCT DATA SHEET

Sikament® NN Hicrete

HIGH RANGE WATER-REDUCING CONCRETE ADMIXTURE

DESCRIPTION

A highly effective water-reducing agent and superplasticizer based on superimposed naphthalene technology for promoting accelerated hardening and free flowing concrete.

USES

Sikament® NN Hicrete as a superplasticizer for flow concrete in :

- Floor slabs
- Foundations
- Slender components with packed reinforcement
- Walls and columns
- Beams and ceilings

Sikament® NN Hicrete as a water-reducer for the manufacture of :

- Pre-cast concrete elements
- Bridges and cantilever structures
- Pre-stressed concrete
- Area of concrete where formwork must be removed quickly or early loading applied.

CHARACTERISTICS / ADVANTAGES

Sikament® NN Hicrete provides the following detail properties :

As a Superplasticizer

Substantial improvement in workability without increased water or the risk of segregation. Normal set without retardation, even when over dosed. Improved density and surface finish.

As a Water Reducer

- Up to 35% water reduction and 40% increase in 28 days strengths.
- Increased frost-resistance.
- Increased watertight.

PRODUCT INFORMATION

Composition	Superimposed naphthalene sulfonate
Packaging	200 L / drum, 1,000 L / tote
Appearance / Colour	Brown
Shelf life	12 months from the date of production If stored properly in undamaged, original, sealed packaging.
Storage conditions	Store in dry conditions, protected from direct sunlight at temperature between 5°C and 40°C.
Density	1.205 - 1.230 kg/l (at temperature 25°C)
pH-Value	7.0 - 10.0 Approx.

APPLICATION INFORMATION

Recommended Dosage	600 - 3,000 cc. per 100 kg. of cement weight. Exact dosage rates are dependent on the type of effect sought, quality of cement and aggregates, water/ cement ratio and ambient temperature. Therefore, in many cases it is advisable to carry out trial mixes. Sikament® NN Hicrete is compatible with all types of Portland Cement, including SRC type and Hydraulic Cement.
Dispensing	Sikament® NN Hicrete can be added separately to the freshly mixed concrete or directly to the mixing water prior to its addition to the aggregates. When added separately to the freshly mixed concrete, further mixing should take place for at least one minute per cubic meter.
Restrictions	Concrete shall be designed in accordance with ACI 211.1-89 standard recommended practice for selecting proportions for concrete and shall contain a super plasticizer which shall be Sikament® NN Hicrete as manufactured by Sika. It shall be used in strict accordance with the manufacturer's recommendations.

IMPORTANT CONSIDERATIONS

Accidental overdosing of Sikament® NN Hicrete may cause segregation. In this case, it is advisable to prolong mixing time until concrete become normal.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited
700/37 Moo 5 Amata City Chonburi
Industrial Estate, T. Klong Tamhru
A. Muang, Chonburi 20000, Thailand
Tel : +66 3810 9500
E-mail : sikathai@th.sika.com
Website: tha.sika.com



Product Data Sheet
Sikament® NN Hicrete
January 2020, Version 01.02
021302011000001089

SikamentNNHicrete-en-TH-(01-2020)-1-2.pdf