

PRODUCT DATA SHEET

SikaLatex[®]-750 Bond

Bonding agent and mortar admixture

DESCRIPTION

SikaLatex[®]-750 Bond is a synthetic rubber emulsion that is used as admixture for cementitious bonding bridges and high quality site-mix mortars.

USES

SikaLatex[®]-750 Bond is used as bonding agent and site-mix mortar admixture for the following applications:

- Grouts and screeds
- Patch repair mortars
- Masonry mortars
- Rendering mortars

FEATURES

The main advantages of SikaLatex[®]-750 Bond are:

- Increased adhesion
- Reduced shrinkage and cracking
- Reduced permeability
- Improved workability
- User friendly
- Suitable on most common construction substrates

PRODUCT INFORMATION

Packaging	25 kg/ pails 200 kg/ drum
Appearance and colour	White liquid
Shelf life	12 months from date of production.
Storage conditions	Store properly in undamaged original sealed packaging, in dry cool conditions at temperatures between 5 °C and 30 °C. Protect from direct sunlight, frost and contamination.
Density	~1.01 kg/l

TECHNICAL INFORMATION

Tensile adhesion strength	(ASTM C1583)		
	Bonding bridge (MPa)	Mortar (MPa)	
	1 day	>0.3	
	7 days	>0.5	
	28 days	>0.8	

APPLICATION INFORMATION

Mixing ratio	1) For Bonding Bridge; SikaLatex®-750 Bond : Cement = 1 kg : 2 kg 2) For Mortar Solution; SikaLatex®-750 Bond : Water = 1:1 to 1:2 (by volume) Dry mix; Cement : Sand = 1:1 to 1:3 (by volume)	
Recommended dosage	Bonding bridge	SikaLatex®-750 Bond : Cement = 1 : 2
	Mortar	SikaLatex®-750 Bond : Water = 1 : 1 to 1 : 2
Pot Life	30 minutes @ 30°C	
Open Time	15 minutes @ 30°C	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

SUBSTRATE PREPARATION

The substrate shall be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by cementitious materials. De-laminated, weak, damaged and deteriorated substrate shall be removed by suitable means before application. Rust, scale, dust and other loose and deleterious materials which reduces bond or contributes to corrosion shall be removed.

MIXING

Mix SikaLatex®-750 Bond with the correct amount of water to produce a gauging solution. Pour part of the gauging solution into a suitable mixing container. While stirring slowly, add the cementsand mix to the gauging solution and mix thoroughly until a smooth, uniform and lump-free mix is achieved. Within the mixing time add additional gauging solution to adjust to the desired consistency.

APPLICATION METHOD / TOOLS

Bonding Bridge/ Mortar

Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and do not allow to dry. Before application remove excess water e.g. with a clean sponge. The surface shall appear a dark matt appearance without glistening and surface pores and pits shall not contain water. Using a stiff clean brush work the mix vigorously onto the substrate, forming a thin layer filling all unevenness, pits and pores. Always apply following layer of mortar "wet on wet" onto bonding bridge.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited

700/37 Moo 5 Amata City Chonburi
Industrial Estate, T. Klong Tamhru
A. Muang, Chonburi 20000, Thailand
Tel : +66 3810 9500
E-mail : sikathai@th.sika.com
Website: tha.sika.com



Product Data Sheet

SikaLatex®-750 Bond

July 2025, Version 01.01
020301010010245082

SikaLatex-750Bond-en-TH-(07-2025)-1-1.pdf