

**BUILDING TRUST** 

# PRODUCT DATA SHEET Sika<sup>®</sup> Plastocrete<sup>®</sup>-570 TH

#### MID-RANGE WATER REDUCING CONCRETE ADMIXTURE

#### DESCRIPTION

Sika<sup>®</sup> Plastocrete<sup>®</sup>-570 TH is a newly modified of midrange water reducing of admixture type for concrete. Sika<sup>®</sup> Plastocrete<sup>®</sup>-570 TH is designed for maximize utilization of low binder content and cost optimization with fly ash 20-35% replacement.

#### USES

- Strength improvement by total cost effectiveness for normal concrete
- Extended workability in high ambient temperature
- Cement saving is required

**PRODUCT INFORMATION** 

• For conventional concrete containing cement replacements such as Fly Ash or Slag

# **CHARACTERISTICS / ADVANTAGES**

Sika<sup>®</sup> Plastocrete<sup>®</sup>-570 TH provided the following properties :

- Equal strength to control mix with less cement
- Beter improvement of early and final strength development
- Compensates for slow early strength gain achieved by cement replacements (PFA, GGBFS)
- Effectively work with cement replacement (PEA, GGBFS)
- Low bleeding when using the high organic content in the aggregate

## **APPROVALS / CERTIFICATES**

Complies with ASTM C494 Type A & D

Packaging	200 l/drum
	1,000 l/tote
Appearance / Colour	Brown Liquid
Shelf life	12 months from the date of production If stored properly in undamaged, original, sealed packaging
Storage conditions	Store in dry conditions, protected from direct sunlight at temperature between 5°C and 40°C.
Density	1.150 - 1.170 kg/l (at temperature 25°C)
pH-Value	8.0 - 10.0 Approx.

Recommended dosage	300-800 cc. per 100 kg of cement or cementitious weight. Actual dosage depends on requirements and should be established from laborat- ory trials. Sika® Plastocrete®-570 TH is compatible with all types of Port- land Cement, including S.R.C. type and Hydraulic Cement.
Dispensing	Sika <sup>®</sup> Plastocrete <sup>®</sup> -570 TH is introduced into the mixer together with mix- ing water.The addition of Sika <sup>®</sup> Plastocrete <sup>®</sup> -570 TH to dry aggregate and cement is not recommended, as it lowers plasticizing effects or the water reduction.

### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### IMPORTANT CONSIDERATIONS

Accidental overdosing of Sika® Plastocrete®-570 TH causes an extention of initial and final setting time.

#### ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited 700/37 Moo 5 Amata City Chonburi Industrial Estate, T. Klong Tamhru A. Muang, Chonburi 20000, Thailand Tel : +66 3810 9500 E-mail : sikathai@th.sika.com Website: tha.sika.com



**Product Data Sheet Sika® Plastocrete®-570 TH** June 2021, Version 01.01 021302011000001210 SikaPlastocrete-570TH-en-TH-(06-2021)-1-1.pdf



**BUILDING TRUST**