

SYSTEM DATA SHEET

Sikafloor® MultiDur ET-56 ESD

Textured conductive epoxy ESD flooring system

DESCRIPTION

Sikafloor® MultiDur ET-56 ESD is an ESD epoxy flooring system with a slip resistant textured finish. The system is designed to dissipate electrostatic charges (ESD) and protect sensitive equipment in electrostatic protected areas (EPA).

USES

Sikafloor® MultiDur ET-56 ESD may only be used by experienced professionals.

Sikafloor® MultiDur ET-57 ESD is used in industrial buildings such as:

- Automotive facilities
- Electronic facilities and data centres
- Pharmaceutical facilities

Please note:

- The System may only be used by experienced professionals.
- The System may only be used for interior applications.

FEATURES

- Good resistance to chemicals
- Electrostatically conductive
- Very good mechanical resistance
- Low VOC emissions
- Low Airborne Molecular Contaminants (AMC) emissions
- Textured gloss finish


CERTIFICATES AND TEST REPORTS

- Fire Classification Report EN 13501-1, GHENT, No. CR 21-0906-01

SYSTEM INFORMATION

System structure

Sikafloor® MultiDur ET-56 ESD



- | | |
|--|---|
| 1. Primer | Sikafloor®-150
Sikafloor®-151
Sikafloor®-156
Sikafloor®-161
Contact Sika Technical Service for information on choosing the right primer for your project. |
| 2. Conductive primer + Earthing connection | Sikafloor®-220 W Conductive + Sikafloor® Conductive Set |
| 3. Conductive wearing layer | Sikafloor®-2350 ESD + Sika® Extender T |

Composition	Epoxy	
Colour	Cured system colour	Available in the approximate colours RAL 1014, RAL 5012, RAL 6000, RAL 6010, RAL 6020, RAL 6021, RAL 6027, RAL 6034, RAL 7001 RAL 7005, RAL 7011, RAL 7021, RAL 7032, RAL 7035, RAL 7036, RAL 7038, RAL 7040, RAL 7045, RAL 7047, RAL 9002
Nominal thickness	~1 mm	

TECHNICAL INFORMATION

Electrostatic behaviour	Resistance to ground	$R_G < 10^9 \Omega$	(IEC 61340-4-1)
	Typical average resistance to ground	$R_G < 10^5\text{--}10^6 \Omega$	
	Body voltage generation	$< 100 \text{ V}$	(IEC 61340-4-5)
	System resistance	$R_G < 10^9 \Omega$	

ESD MEASUREMENT CONDITIONS AND SPECIFICATIONS

All measurement values for the system stated in the System Data Sheet (except those referring to proof statements) were measured using the following equipment and ambient conditions:

Condition or Equipment	Specification
Size of ESD-footwear	42 (EU) (UK: 8; US: 8.5)
Test person weight	90 kg
Ambient conditions	+23 °C and 50 % relative humidity
Measuring device for measuring resistance to ground	Metriso 2000 or 3000 (Warmbier) or comparable
Surface resistance probe	Carbon Rubber electrode. Weight: 2.50 kg
Rubber pad hardness	Shore A (60 ±10)
Measuring device for measuring body voltage generation	Walking Test Kit WT 5000 (Warmbier) or comparable

IMPORTANT

ESD footwear requirements

The ESD shoes used in the EPA must have a resistance of $< 5 \text{ MOhm}$ according to IEC 61340-4-3 at climate class 1 (12 % relative humidity and +23 °C). In order to achieve charges of $< 30 \text{ volts}$ of human body charge during the walking test (at 12 % relative humidity and +23 °C), we recommend using the following ESD shoes: Weeger ESD clog, art. 48512-30, www.schuhweeger.de.

Note: Measurement results can be affected by ESD clothing, ambient conditions, measurement equipment, cleanliness of the floor and the test personnel.

Service temperature	Short-term, maximum 12 hours	+60 °C
----------------------------	------------------------------	--------

IMPORTANT

Simultaneous mechanical and chemical strain

While the Product is exposed to temperatures up to +60 °C, simultaneous mechanical or chemical strain may cause damage to the Product.

1. Do not expose the Product to chemical or mechanical strain at elevated temperatures



APPLICATION INFORMATION

Consumption	Layer	Product	Consumption
	Primer	Sikafloor®-150	1-2 × 0.3–0.5 kg/m ²
		Sikafloor®-151	
		Sikafloor®-156	
		Sikafloor®-161	
Levelling		Sikafloor®-150	Refer to the individual Product Data Sheet.
		Sikafloor®-151	
		Sikafloor®-156	
		Sikafloor®-161	
Earthing connection		Sikafloor® Conductive Set	1 earthing point per 200–300 m ² , minimum 2 per room.
Conductive primer		Sikafloor®-220 W Conductive	0.08–0.10 kg/m ²
Conductive wearing layer		Sikafloor®-2350 ESD + Sika® Extender T	~0.8 kg/m ² + 2 % by Sika® Extender T weight

Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply the Product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.

Ambient air temperature	Maximum	+30 °C
	Minimum	+15 °C

Relative air humidity	Maximum	80 % r.h.
-----------------------	---------	-----------

Dew point	Refer to the individual Product Data Sheet.	
-----------	---	--

Substrate temperature	Maximum	+30 °C
	Minimum	+15 °C

Substrate moisture content	Refer to the individual Product Data Sheet.	
----------------------------	---	--

Waiting time to overcoating	For the waiting time to overcoating of the primer, refer to the individual Product Data Sheet.		
	Before applying Sikafloor®-2350 ESD on Sikafloor®-220 W Conductive, allow:		
	Temperature	Minimum	Maximum
	+15 °C	~26 hours	~7 days
	+20 °C	~17 hours	~5 days
+30 °C	~12 hours	~4 days	

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

Applied product ready for use	Temperature	Foot traffic	Light traffic	Full cure
	+15 °C	~48 hours	~3 days	~7 days
	+20 °C	~24 hours	~48 hours	~4 days
	+30 °C	~16 hours	~36 hours	~3 days

Note: Times apply when the last layer of the system has been applied. Times are affected by changing ambient conditions, particularly temperature and relative humidity.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

Refer to the following method statements:

- Sika Method Statement — Evaluation and preparation of surfaces for flooring systems
- Sika Method Statement — Sikafloor® mixing and application

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

APPLICATION

ESD CONDUCTIVITY MEASUREMENTS

Recommended number of conductivity measurements is specified in the following table:

<u>Ready applied area</u>	<u>Number of measurements</u>
< 10 m ²	6
≥ 10 m ² and < 100 m ²	10 to 20
≥ 100 m ² and < 1000 m ²	50
≥ 1000 m ² and < 5000 m ²	100

If the measurements yield values that are outside of the agreed specification, follow these steps:

1. Carry out one additional measurement within a radius of approximately 30 cm around the original measuring point.

If the value of the new measurement meets the agreed specification, the original measurement can be disregarded.

If the value of the new measurement does not meet the agreed specification, repeat the measurement described above until the fulfilment of the requirements have been verified.

If the requirements cannot be verified, contact Sika Technical Services.

INSTALLATION OF EARTHING POINTS

Refer to Sika Method Statement: Sika Method Statement — Sikafloor® mixing and application
Number of earthing connections per room: Minimum of 2 earthing connections. The optimum number of earthing connections depends on the local conditions and must be specified on drawings or other contract documentation.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited

700/37 Moo 5 Amata City Chonburi
Industrial Estate, T. Klong Tamhru
A. Muang, Chonburi 20000, Thailand
Tel : +66 3810 9500
E-mail : sikathai@th.sika.com
Website: tha.sika.com



System Data Sheet

Sikafloor® MultiDur ET-56 ESD
September 2024, Version 07.01
020811900000000192

SikafloorMultiDurET-56ESD-en-TH-(09-2024)-7-1.pdf