

**BUILDING TRUST** 

# PRODUCT DATA SHEET SikaGrind<sup>®</sup> VRM-40 S-02/R1

### GRINDING AID FOR THE PRODUCTION OF CEMENT

### DESCRIPTION

SikaGrind<sup>®</sup> VRM-40-S02/R1 is a chloride free, liquid cement additive.

### USES

•Increase the production rate of cement

### **CHARACTERISTICS / ADVANTAGES**

## SikaGrind<sup>®</sup> VRM-40-S02/R1 provides the following advantages in the cement production:

•Increased production rate

•Reduced vibration and wear

•Increased stability of the material bed on the grinding table

•Improved de-aeration of the material bed under the roller

•Easier achievement of the desired cement fineness •Cost savings due to lower specific power consump-

tion per ton

## SikaGrind<sup>®</sup> VRM-40-S02/R1 gives the following advantages to the finished cement:

•Improved particle size distribution

•Improved powder flow characteristics and easier discharge of silos

•Improved cement quality by the reduction of water injection

### **PRODUCT INFORMATION**

Packaging	1,000 kg IBC
Appearance / Colour	Colourless liquid
Shelf life	At least 12 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Stored at temperatures between +5°C and +35°C. Protect from frost, direct sunlight and contamination. Note: When delivered in bulk, the tanks and equipment used must be free from contaminants.
Density	1.010 - 1.030 kg/L (at +25°C)
Viscosity	30 - 50 mPa.s (25 °C)

Product Data Sheet SikaGrind® VRM-40 S-02/R1 February 2019, Version 01.01 021407011000000342

Recommended Dosage	Typical dosage rates of SikaGrind® VRM-40-S02/R1 are between 0.1 - 0.5 kg per ton of cement (0.01% - 0.05% of total weight = cement clinker + addi- tions). The optimum dosage to achieve the desired characteristics shall be determined in plant trials. Influencing factors are e.g. the properties of clinker, type of cement and other plant variables.
Compatibility	Cements treated with SikaGrind <sup>®</sup> VRM-40-S02/R1 are compatible in con- cretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of con- crete admixtures are not adversely affected by the use of SikaGrind <sup>®</sup> VRM- 40-S02/R1.
Dispensing	SikaGrind® VRM-40-S02/R1 is added onto the clinker feed shortly before the mill entrance or sprayed directly into the grinding mill on the material bed. Suitable dosage pumps with adjustable flow rates shall be used for ac- curate dosing. Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked!

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

### ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika (Thailand) Limited 700/37 Moo 5 Amata City Chonburi KM.57 Bangna Trad Rd., T. Klong Tamhru A. Muang, Chonburi 20000, Thailand Tel : +66 3810 9500 E-mail : sikathai@th.sika.com www.sika.co.th



Product Data Sheet SikaGrind® VRM-40 S-02/R1 February 2019, Version 01.01 021407011000000342 SikaGrindVRM-40S-02R1-en-TH-(02-2019)-1-1.pdf



**BUILDING TRUST**